

IN THE CLAIMS:

Please amend the claims as follows.

1. (Currently Amended) A method for evaluating a capacity ~~the performance~~ of an anion exchange resin, wherein the capacity is reduced over time, comprising the steps of:  
measuring an inorganic carbonic acid concentration in an outlet water of an ion exchange resin vessel filled with at least an anion exchange resin, by using an electric conductivity sensor with a gas permeation membrane, thereby avoiding influences from other acid ions; and  
evaluating a performance of the anion exchange resin filled in said ion exchange resin vessel based on the measured inorganic carbonic acid concentration in the outlet water,  
wherein the anion exchange resin demineralizes raw water and the capacity of the anion exchange resin for demineralizing raw water is reduced over time.
2. (Previously Presented) The method according to claim 1, further comprising the steps of:  
measuring an inorganic carbonic acid concentration in an inlet water of said ion exchange resin vessel; and  
evaluating the performance of said anion exchange resin based on the inorganic carbonic acid concentrations of said outlet water and of said inlet water.
3. (Previously Presented) The method according to claim 1, wherein said inorganic carbonic acid concentration is continuously measured.
4. (Previously Presented) The method according to claim 1, wherein said inorganic carbonic acid concentration is intermittently measured.
5. (Previously Presented) The method according to claim 2, further comprising the steps of:  
calculating an MTC (Mass Transfer Coefficient) of said anion exchange resin with respect to the inorganic carbonic acid from the measured inorganic carbonic acid concentrations of the inlet water and of the outlet water of said ion exchange resin vessel; and  
evaluating the performance of said anion exchange resin based on the obtained MTC.

6. (Previously Presented) The method according to claim 5, further comprising the steps of:  
evaluating a degree of degradation of said anion exchange resin from said MTC; and  
judging at least one of a replacement timing, a lifetime, and a throughput capacity for  
said anion exchange resin.
- 7.-13. (Cancelled)
14. (Currently Amended) A ~~performance~~ capacity evaluation apparatus for anion exchange  
resins, comprising:  
an outlet monitoring device for measuring an inorganic carbonic acid concentration of an  
outlet water of an ion exchange resin vessel filled with an anion exchange resin,  
by using an electric conductivity sensor with a gas permeation membrane, thereby  
avoiding influences from other acid ions; and  
an evaluation device for evaluating a performance of the anion exchange resin filling said  
ion exchange resin vessel based on the measured inorganic carbonic acid  
concentration of the outlet water measured by said monitoring device,  
wherein the anion exchange resin demineralizes raw water and the capacity of the anion  
exchange resin for demineralizing raw water is reduced over time.
15. (Previously Presented) The apparatus according to claim 14, further comprising:  
an inlet monitoring device for measuring an inorganic carbonic acid concentration of an  
inlet water of said ion exchange resin vessel; wherein said evaluation device  
evaluates a performance of said anion exchange resin based on the inorganic  
carbonic acid concentrations of said outlet water and of said inlet water.
16. (Previously Presented) The apparatus according to claim 14, wherein said outlet monitoring  
device continuously measures the inorganic carbonic acid concentration of said outlet water.
17. (Previously Presented) The apparatus according to claim 14, wherein said outlet monitoring  
device intermittently measures the inorganic carbonic acid concentration of said outlet water.

18. (Previously Presented) The apparatus according to claim 15, wherein said evaluation apparatus calculates MTC (Mass Transfer Coefficient) of said anion exchange resin with respect to the inorganic carbonic acid from the measured inorganic carbonic acid concentrations of the inlet water and of the outlet water of said ion exchange resin vessel, and evaluates the performance of the anion exchange resin based on the obtained MTC.
19. (Previously Presented) The apparatus according to claim 18, wherein said evaluation apparatus evaluates a degree of degradation of the anion exchange resin from said MTC and judges at least one of a replacement timing, a lifetime, and a throughput capacity for said anion exchange resin.
20. (Previously Presented) The apparatus according to claim 14, wherein said ion exchange resin vessel is a condensate water demineralization vessel of a condensate water demineralization system.
- 21.-23. (Cancelled)